

## CONDUCTIVE PASTE

Patent number: JP5234414  
Publication date: 1993-09-10  
Inventor: TANI KOJI; others: 01  
Applicant: MURATA MFG CO LTD  
Classification:  
- International: H01B1/16; H01B1/22; H01G4/12  
- european:  
Application number: JP19920033191 19920220  
Priority number(s):

### Abstract of JP5234414

**PURPOSE:** To prevent generation of a warp and a crack on a chip element so as to improve an yield of a product by dispersing a specific amount of copper powder in an organic vehicle.  
**CONSTITUTION:** Copper powder 40 to 70wt.% is dispersed in an organic vehicle so as to obtain a conductive paste. Since this paste is made into a glass fritless containing no glass frit having a large coefficient of heat contraction, the coefficient of heat contraction is small resulting in thinner coat. Further, generation of firing blister in an outer electrode can be suppressed.

Data supplied from the esp@cenet database - Patent Abstracts of Japan